



**FIRE  
TECHNOLOGY  
SERVICES**

## **Confidential Report**

**Our Ref: 27/02809C/05/13**

Notified Body  
for PPE Directive,  
Construction Products Directive  
& Marine Equipment Directive  
I.D. No. 0338 & 0339

**Fire Technology Services  
A division of BTTG T & C Ltd  
Wira House, West Park Ring Road,  
Leeds, LS16 6QL**



**1066**

**Tel No: +44 (0)113 25919969 Fax No: +44 (0)113 2780306**



**FIRE  
TECHNOLOGY  
SERVICES**

BTTG Testing & Certification Ltd.  
Wira House  
West Park Ring Road  
Leeds, LS16 6QL  
England

Tel: +44 (0)113 259 1999  
Fax: +44 (0)113 278 0306  
Web: <http://www.bttg.co.uk>  
Email: [CSLeeds@bttg.co.uk](mailto:CSLeeds@bttg.co.uk)

26 June 2013

Our Ref: 27/02809C/05/13  
Your Ref:

Page 1 of 4

Client: Eco-Sol Ltd  
Cardiff House  
Cardiff Road  
Barry  
Vale of Glamorgan  
CF63 2AW

Job Title: **Fire Test on One Sample of Fabric**

Clients Order Ref: ---

Date of Receipt: 10 May 2013

Description of Sample: One sample of fabric, referenced: **Linen 440 g/m<sup>2</sup>**.

Work Requested: Fire Technology Services were requested to carry out a fire test on the sample supplied to IMO FTP Code 2010:Part 7.





**FIRE  
TECHNOLOGY  
SERVICES**

BTTG Testing & Certification Ltd.  
Wira House  
West Park Ring Road  
Leeds, LS16 6QL  
England

Tel: +44 (0)113 259 1999  
Fax: +44 (0)113 278 0306  
Web: <http://www.bttg.co.uk>  
Email: [CSLeeds@bttg.co.uk](mailto:CSLeeds@bttg.co.uk)

26 June 2013

Page 2 of 4

Our Ref: 27/02809C/05/13  
Your Ref:

Eco-Sol Ltd

**FIRE TESTS ACCORDING to IMO FTP Code 2010:Part 7  
Test for Vertically Supported Textiles and Films**

**Date of Test:** 17/06/13

**Cleaning Procedure**

The sample was subjected to 10 accelerated dry cleaning cycles as specified in the IMO FTP Code 2010:Part 7 Appendix 3. The sample was submitted to an external dry cleaning company.

**Conditioning**

The sample was conditioned for 72 hours in the standard atmosphere for conditioning textiles of  $20 \pm 5^\circ\text{C}$  and  $65 \pm 5\%$  R.H.

**Procedure**

The sample was tested in accordance with IMO FTP Code 2010:Part 7. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

A 40mm high propane gas flame was applied to the face of 5 warp and 5 weft specimens for 5 seconds.

The after-flame time, length of char, existence of surface flashing and ignition of cotton waste from drops were recorded.





26 June 2013

Page 3 of 4

Our Ref: 27/02809C/05/13  
Your Ref:

Eco-Sol Ltd

**Requirements**

Appendix 3 of the above document: Proposed Criteria for Curtains and Drapes, states that: Products which show any of the following characteristics should be considered unsuitable for use as curtains, drapes or free-hanging fabric product for use in rooms containing furniture and furnishings of restricted fire risk.

1. An after-flame time greater than 5 sec with surface application of the pilot flame.
2. Burn through to any edge with surface application of the pilot flame.
3. Ignition of cotton wool below specimen.
4. An average char length in excess of 150mm.
5. The occurrence of a surface flash propagating more than 100mm from the point of ignition.
6. If one of any of the five specimens in each direction fails to meet the above criteria, one complete re-test of a similar batch is permitted. Failure of the second batch to meet any of the criteria should provide the basis for rejection of the fabric for use.

**Results**

The test results relate to the behaviour of the test specimen of a product under the particular conditions of the test; they are not intended to be the sole criteria for assessing the potential fire hazard of the product in use.

	After flame time (s)		Char length (mm)		Burning Droplets (Yes or No)		Flaming to edge (yes or No)	
	Warp	Weft	Warp	Weft	Warp	Weft	Warp	Weft
	0	0	62	85	No	No	No	No
	0	0	60	90	No	No	No	No
	0	0	50	80	No	No	No	No
	0	0	45	83	No	No	No	No
	0	0	80	65	No	No	No	No
Mean	0	0	59	81				





**FIRE  
TECHNOLOGY  
SERVICES**

BTTG Testing & Certification Ltd.  
Wira House  
West Park Ring Road  
Leeds, LS16 6QL  
England

Tel: +44 (0)113 259 1999  
Fax: +44 (0)113 278 0306  
Web: <http://www.bttg.co.uk>  
Email: [CSLeeds@bttg.co.uk](mailto:CSLeeds@bttg.co.uk)

26 June 2013

Page 4 of 4

Our Ref: 27/02809C/05/13  
Your Ref:

Eco-Sol Ltd

**Comment**

In our opinion, based on the test carried out on the sample supplied; the results indicate the sample meets the requirements according to IMO 2010 FTP Code, Part 7.

Reported by:..... *B Marsden* ..... B Marsden (Mrs), Fire Technician

Countersigned by:..... *P Doherty* ..... P Doherty, Operational Head

Enquiries concerning this report should be addressed to Customer Services.

